Black Pearl 5mm



Black Pearl is a carpet underlay produced from flat sponge rubber. The heavy sponge rubber creates a stable and durable base for every carpet. Black Pearl delivers a maximum contribution to the experience of luxury and comfort of the carpet. Black Pearl is suitable for domestic and H.D. contract applications.

- Stable base for installation and easy process
- smoothening small unevenness in the subfloor
- Extends the lifetime and original appearance of the carpet
- Especially suitable for floor heating

Installation method: Double stick method. Install Black Pearl with the spongerubber side in a non slip

adhesives and glue the carpet on top of the crepe paper topside. Black Pearl is also

suitable for the stretching method.

Direction of installation method: Always install the underlay in a 90 angle underneath the length of the carpet in

order to avoid matching of seams in underlay and carpet.

General building inspection NA

license:

Thickness:

5 mm / \pm 0,5 mm - maximum tolerance 10%

Dimensions: $7,3m \times 1,37m = \pm 10m^2$

Weight: $2700 \text{ gr/m}^2 / \pm 270 \text{ gr/m}^2 (27 \text{ kg/roll}) - \text{maximum tolerance } 10\%$

Density: $540 \text{ kg/m}^3 / \pm 54 \text{ kg} - \text{maximum tolerance } 10\%$

Material: Top Layer: Stitch bonded perforated crepe paper

Middle Layer: Flat sponge Rubber
Bottom Layer: Polypropylene non-woven

Packing: Material: Printed LDPE foil (no core) with insert sheet.



Black Pearl 5mm



Technical information:

Dimensional stability Traction : 40 N/mm² /lenght 280N / width 160N

Dimensional stability extension: : 10% / lenght 0,8% / width 0,5%

(Test method: ISO 13934-1)

(Test method: NA)

Caster chair test : none (Test method: EN 985)

Impact sound reduction : ΔLw = 26 dB

Thermal resistance : 0,55 togs - 0,055m² K/W

(Test method: NA)

Fire retardency : Bfl-S1 (Test method: EN 13501-1 (2007) + A1 (2013)

ASTM radial panel test : Class 1

(Test method: ASTM E 648-06)

Russian requirements on fire safety : Class KM5 (Test method: FZ-123)

Installation instructions:

• Let the carpet as well as the underpadding acclimatise for 24 hours in the original packing in the room to be installed.

The best temperature for installation is 5-20°C. and a humidity of 50-70%.

• make sure that the underfloor is absolutely dry and free of grit and dust.

• To cut the underpadding we recommend to use a trapezium blade.

• Underpadding can not prevant the natural shrinkage of carpet. For that reason we strongly advise <u>always</u> to use the double stick method (gluing both the underpadding as well as the carpet) in case of shrink-sensible qualities.

• Always follow the installation advice of the carpet manufacturer and adhesive supplier in order to avoid problems during installation.

Important:

If the installation instructions are not followed correctly, Estillon can not be held liable for damage and / or claims resulting from incorrect installation. If in doubt, consult your supplier.



