



BELFLOR SDN Action Back

version 02.03.2023
replaces 21.02.2023

Manufacturing type	Herstellungsart	Mode fabrication	Productie methode	tufted 1/8"		
Construction	Struktur	Structure	Structuur	2-ply cut pile		
Pile composition	Polmaterial	Couche d'usure	Poolsamenstelling	100% PA 6		
Dye method	Farbgestaltung	Coloration	Kleurverwerking	solution dyed		
Primary backing	Trägermaterial	Premier dossier	Tuftdoek	woven		
Secondary backing	Rückenausrüstung	Dossier	Rug	action backing		
Pile weight	Poleinsatzgewicht	Poids de velour	Poolgewicht	ISO 2424	g/m2	810 (+/-)
Total weight	Gesamtgewicht	Poids total	Totaal gewicht	ISO 8543	g/m2	1.900 (+/-)
Pile height	Polhöhe	Hauteur du velours	Poolhoogte	ISO 1766	mm	5,5 (+/-)
Total height	Gesamtdicke	Epaisseur totale	Totale dikte	ISO 1765	mm	7,0 (+/-)
Tuft density	Noppenzahl	Nombre de touffes	Aantal punten	ISO 1763	/m2	123.500 (+/-)
Width	Breite	Largeur	Breedte		cm	400 (+/-)
Classification	Klassifikation	Classement	Gebruiksklasse	EN 1307	32	general commercial
Comfort rating	Komfortklasse	Classement confort	Comfort klasse	EN 1307	LC 3	
Castor chair	Stuhlleneignung	Chaise à roulettes	Rolstoelgeschikt	EN 985		
Stair suitability	Treppeneignung	Escaliers	Trappengeschikt	EN 1963	A	intensive
Fire resistance	Brennverhalten	Comportement feu	Brandgedrag	EN 13501-1	Cfl-S1	glued
Permanent antistatic	Permanent Antistatisch	Antistatique permanent	Permanent antistatisch	ISO 6356	kV	≤ 2,0
Transversal resistance	Durchgangswiderstand	Résistance transversale	Doorgangsweerstand	ISO 10965	Ω	≥ 10 ¹⁰
Thermal resistance	Wärmedurchlaßwiderstand	Résistance thermique	Warmtedoorlaatweerstand	ISO 8302	m2/K/W	0,100
Sound absorption	Schallabsorptionsgrad	Absorption phonique	Geluidsabsorptie	ISO 354	α _w	0,20
Impact sound reduction	Trittschallverbesserungsmaß	Isolation phonique	Geluidsisolatie	ISO 10140	ΔL _w	22 dB
				ISO 10140	ΔL	32 dB (1000 Hz)
Light fastness	Lichtechtheit	Solidité à la lumière	Lichtechtheid	ISO 105 B02		≥ 7
Rubbing fastness	Reibechtheit	Solidité au frottement	Wrijftechtheid	ISO 105 X12		≥ 5 wet/dry
Water fastness	Wasserechtheit	Solidité à l'eau	Waterechtheid	ISO 105 E01		colour/staining



 23 EN 14041 DOP 000636A-001	 Cfl-S1
	 DS
TAPIBEL NV Industrielaan 4 B-3900 Pelt Belgium +32 11 80 48 50 sales@tapibel.be www.tapibel.be	 DL
	 PCP
 NA HCHO	
EN 1307 for use as floorcovering in buildings (EN 14041) according to the manufacturer's specification	



MAINTENANCE - INSTALLATION

download our technical guidelines via www.tapibel.be or contact the sales desk

These technical details are approximate. Complete specification details and associated certificates together with tolerances applying to the above can be provided upon request, if available.

We reserve the right to alter specifications without notice.

Due to the method of manufacture, perfect pattern/colour matching cannot be guaranteed.

Shading/pile reversal might occur in cut pile carpets, without affecting overall quality and suitability. It is not considered as a manufacturing fault.